

Aggregate Industries...  
Marston House,  
Marston Bigot,  
FROME,  
Somerset,  
BA11 5DU  
Contract: Torr

Date: 20 August 2015  
Test Report Ref: STR 426996  
Order No: 7056520  
Page 1 of 1

### LABORATORY TEST REPORT

**TEST REQUIREMENTS:** To determine the Ten Per Cent Fines Value (TFV) of aggregate sample 10mm and greater in accordance with **BS 812: Part 111: 1990.**

#### **SAMPLE DETAILS:**

Certificate of sampling received:	<b>Yes</b>
Laboratory Ref. No:	<b>S54142</b>
Client Ref. No:	<b>Aggs21772 - 63181C</b>
Date and Time of Sampling:	<b>03/08/2015 (06:30)</b>
Date of Receipt at Lab:	<b>11/08/2015</b>
Date of Start of Test:	<b>20/08/2015</b>
Sampling Location:	<b>Current Production Belt</b>
Name of Source:	<b>Torr Works</b>
Method of Sampling:	<b>Unknown</b>
Sampled By:	<b>Client</b>
Material Description:	<b>6/14mm SS Carboniferous Limestone</b>
Target Specification	<b>N/A</b>

#### **RESULTS:**

Ten per cent fines value (DRY) = **190 kN**

#### **Comments**

Has the "as received material" been altered by crushing in the laboratory: **No**

Report to nearest 10kN for forces of 100kN or more report to nearest 5kN for forces less than 100kN.

Certificate  
Prepared by:-

  
Neil Hughes

Job Coordinator

Approved by: - 

Eric Goulden  
Technical Manager